

Claims

1. Polycarbonate substrates, the preparation of which is based on 1,1-bis-(4-hydroxyphenyl)-3,3,5-trimethylcyclohexanone, with fewer than 300 defects per m², measured on a 200 µm extruded film.
5
2. Polycarbonate substrates, the preparation of which is based on 1,1-bis-(4-hydroxyphenyl)-3,3,5-trimethylcyclohexanone, with fewer than 250 defects per m², measured on a 200 µm extruded film
10
3. Use of the polycarbonate substrates as defined in any of the preceding claims to produce polycarbonate shaped articles.
4. A process for the preparation of polycarbonate shaped articles with a small number of defects, characterised in that polycarbonate substrates as defined in claim 1 or 2 are used as the starting substrates.
15
5. Shaped articles prepared from polycarbonate based on 1,1-bis-(4-hydroxyphenyl)-3,3,5-trimethylcyclohexanone, with fewer than 300 defects per m², measured on a 200 µm extruded film.
20
6. Shaped articles according to claim 5 with a cloudiness of less than 0.5 %.
7. Disks produced from polycarbonate based on 1,1-bis-(4-hydroxyphenyl)-3,3,5-trimethylcyclohexanone, with fewer than 300 defects per m², measured on a 200 µm extruded film and with a cloudiness of less than 0.5 %.
25
8. Sheets produced from polycarbonate based on 1,1-bis-(4-hydroxyphenyl)-3,3,5-trimethylcyclohexanone, with fewer than 300 defects per m², measured on a 200 µm extruded film and with a cloudiness of less than 0.5 %.
30